

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08L 23/08, 23/12, 51/06, E04F 15/10		A1	(11) International Publication Number: WO 97/10298 (43) International Publication Date: 20 March 1997 (20.03.97)
(21) International Application Number: PCT/SE96/01094 (22) International Filing Date: 4 September 1996 (04.09.96) (30) Priority Data: 9503197-7 15 September 1995 (15.09.95) SE (71) Applicant (for all designated States except US): TARKETT AB [SE/SE]; S-372 81 Ronneby (SE). (72) Inventor; and (75) Inventor/Applicant (for US only): LUNDQUIST, Eskil [SE/SE]; Bondevägen 6, S-372 33 Ronneby (SE). (74) Agent: AWAPATENT AB; P.O. Box 5117, S-200 71 Malmö (SE).			(81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FLOORING MATERIAL			
(57) Abstract <p>A flooring material comprises 30-70 parts by weight of a copolymer of ethylene and an α-olefin having 4-10 carbon atoms, preferably an ethylene/octene copolymer, 20-40 parts by weight of polypropylene, 5-20 parts by weight of a cross-linked ethylene polymer, preferably a copolymer of ethylene and an ethylenically unsaturated silane compound, 10-25 parts by weight of an organic filler, preferably polyethylene having a melt index below 0.1 g/10 min (190 °C/21.6 kg) and a phase stability in the flooring material of at least about 200 °C, 0.2-7 parts by weight of a flame retardant, preferably silicone and magnesium stearate, 0.1-2 parts by weight of an antistatic agent, and 0.1-1 part by weight of a stabiliser. The flooring material is free from inorganic fillers.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

FLOORING MATERIAL

The invention relates to a flooring material, and more specifically concerns a halogen-free flooring material that is free from inorganic fillers.

In order to be acceptable, a flooring material has
5 to possess a number of different properties, which are more or less incompatible. One such property is processibility, i.e. it has to be possible to process the material so as to form it into a sheetlike or weblike flooring material. In this context, it is of primary importance
10 tance that the material is easily calendered. Furthermore, the flooring material should be wear- and scratch-resistant, and its surface should exhibit such friction as to be suited for use, for instance by people walking on it. In addition, the material should be weldable,
15 enabling the provision of tight joints when putting down a floor. The flooring material should, moreover, enable optimum cleaning, and should thus be polishable and preferably have a dirt-repellent surface. The resilience and the softness of the flooring material, which are measured
20 by indentation-recovery, are essential qualities, which are of importance in order to avoid lasting indentations of furniture and rolling objects, such as office chairs, and which also affect the walking comfort. Moreover, the fire resistance is vital, and the flooring material
25 should be as fire-resistant as possible while, if catching fire, giving off as little irritant smoke as possible.

Using polyvinyl-chloride-based materials, such as polyvinyl chloride (PVC) and vinyl chloride copolymers,
30 primarily copolymers of vinyl chloride and vinyl acetate, as flooring materials is previously known. These materials have many advantages, such as fetching a low price, being easy to process, and having a great range of variation, i.e. the properties of the material are easily

adjusted with the aid of various additives, such as plasticisers and pigments.

However, PVC-based flooring materials also suffer from a number of drawbacks. In recent years, attention
5 has focused on these drawbacks, and efforts have been made to provide other synthetic flooring materials not based on PVC. Among other things, PVC-based flooring materials are disadvantageous in that they contain chlorine (halogen), which forms hydrogen chloride upon combustion. Also, the various additives included in PVC-
10 based flooring materials and typically containing different metal compounds yield metal-containing residues when combusted. For reasons of costs and properties, PVC-based flooring materials further contain considerable amounts
15 of fillers which generally are of inorganic type, such as calcium carbonate, clays, and aluminium trihydrate. These inorganic fillers are non-combustible and thus leave a contaminating residue, which has to be deposited, when the flooring material is combusted. When PVC-based flooring materials are combusted, various additives, such as
20 lime or dolomite, are used for binding released chlorine. As a result, larger amounts of material have to be deposited, and the costs are increased.

Also, an addition of inorganic fillers has an
25 adverse effect on the wear resistance of the material.

In an effort to obviate the above-mentioned drawbacks of the PVC-based flooring materials, one has, in recent years, tried to develop halogen-free flooring materials, which usually are based on different mixtures
30 of olefin polymers. US Patent 5,276,082 teaches such a halogen-free flooring material, which comprises a mixture of a silane-grafted polymer and an ungrafted polymer. To be more specific, the mixture contains a first component, which is a copolymer of ethylene and another monomer
35 selected from the vinyl esters of saturated and unsaturated carboxylic acids, preferably vinyl acetate, and a second component, which consists of a silane-grafted ver-

sion of the above-mentioned ethylene copolymer, i.e. preferably silane-grafted ethylene/vinyl acetate. A third essential component of the mixture is a filler, preferably calcium carbonate, clay or aluminium trihydrate,
5 which is present in an amount of 30-90% by weight.

Even though the flooring material according to US Patent 5,276,082 is free from halogen, it has, like other prior-art flooring materials, a high content of inorganic fillers, which result in the formation of environmentally
10 questionable or objectionable metal-containing substances and ash when destroyed by combustion of the flooring material.

This invention aims at obviating the drawbacks of the prior art by providing a halogen-free flooring material which is not based on PVC and, in addition, is free
15 from inorganic fillers.

According to the invention, this aim is achieved by a flooring material comprising a defined composition of olefin polymers in combination with an organic filler and
20 certain additives.

To be more specific, the invention provides a flooring material which is characterised in that it comprises 30-70 parts by weight of a copolymer of ethylene and an α -olefin having 4-10 carbon atoms,
25 20-40 parts by weight of polypropylene,
5-20 parts by weight of a crosslinked ethylene polymer,
10-25 parts by weight of an organic filler,
0.2-7 parts by weight of a flame retardant,
0.1-2 parts by weight of an antistatic agent, and
30 0.1-1 part by weight of a stabiliser,
and that the material is free from inorganic fillers.

Preferably, the flooring material according to the invention comprises
40-60 parts by weight of a copolymer of ethylene and an
35 α -olefin having 4-10 carbon atoms,
25-30 parts by weight of polypropylene,
5-15 parts by weight of a crosslinked ethylene polymer,

10-20 parts by weight of an organic filler,
0.6-4 parts by weight of a flame retardant,
0.1-1 part by weight of an antistatic agent, and
0.1-1 part by weight of a stabiliser.

5 These and other distinctive features and advantages of the invention will appear in more detail from the following description as well as the appended claims.

As indicated above, the flooring material according to the invention contains a first component in the form
10 of 30-70 parts by weight, preferably 40-60 parts by weight, of a copolymer of ethylene and an α -olefin having 4-10 carbon atoms. This component is intended to impart elasticity to the material and to reduce its melting temperature, resulting in a wider temperature range for
15 processing and hence improving the processibility of the material. The copolymer also improves the properties of the flooring material as regards wear resistance and indentation-recovery. In order to attain an aimed-at processing range of about 150-200°C, the melting point of
20 the copolymer should be below 120°C, preferably ranging between about 50°C and 100°C. The density of the copolymer is about 0.87-0.92 g/cm³. Octene is a preferred α -olefin comonomer, and an instance of a preferred copolymer is the ethylene/octene copolymer available from Dow
25 under the designation DSH 8501.00.

As a second component, the flooring material according to the invention contains 20-40 parts by weight of polypropylene, preferably 25-30 parts by weight. This component enhances the hardness of the material and
30 reduces its friction. In addition, the dirt-repellent qualities of the material are improved, i.e. the flooring material becomes easier to clean. An example of a preferred propylene polymer is the one available from Borealis AB under the tradename of Embryon[®] HG 770 J
35 having a density of 0.903 g/cm³ and a melt flow of 25 g/10 min (230°C/2.16 kg).

As a third component, the flooring material according to the invention contains 5-20 parts by weight, preferably 5-15 parts by weight, of a crosslinked ethylene polymer, preferably a silane-crosslinked ethylene polymer. The preferred silane-crosslinked ethylene polymer may consist of either a graft copolymer of ethylene and an ethylenically unsaturated, hydrolysable silane compound or, which is preferred, a copolymer of ethylene and an ethylenically unsaturated, hydrolysable silane compound. As silane compound, use may, for instance, be made of vinyl silanes, such as vinyl trimethoxy silane. Such silane (graft) copolymers are crosslinked under the action of water and a silanol condensation catalyst, such as dibutyltin dilaurate. The crosslinked ethylene polymer component improves the processing properties of the mixture by increasing the viscosity of the material and hence reducing the mobility therein, thereby facilitating the achievement of the aimed-at patterns. Furthermore, the crosslinked ethylene polymer improves the properties of the material as regards wear and indentation-recovery. In order to optimise the effect of the crosslinked ethylene polymer component in the composition, the degree of crosslinking should not be too high. Preferably, the silane compound constitutes about 1-30% by weight, preferably about 1-15% by weight, of the crosslinked ethylene polymer. As an example of a preferred crosslinkable ethylene polymer, mention may be made of the products LE 4421 and LE 4438 available from Borealis AB. The former is the polymer itself, whereas the latter is the crosslinking catalyst.

As a fourth component, the flooring material according to the invention contains 10-25 parts by weight, preferably 10-20 parts by weight, of an organic filler. By the term "organic filler" is meant an organic material which, upon combustion, leaves a residue of no more than 10% by weight, preferably no more than 5% by weight, and which preferably consists chiefly, i.e. to at least 95%

by weight, of carbon, hydrogen and oxygen. According to the invention, this organic filler is intended to replace, either by itself or in combination with the other components, the inorganic fillers generally used in prior-art flooring materials. In order to be able to perform its function properly, the organic filler should be phase-stable, i.e. form a phase of its own in the form of discrete particles in the flooring material, when the flooring material is being processed. Since the flooring material is normally processed at a temperature below about 200°C, this means that the organic filler should be phase-stable or "particle-stable", i.e. be present in the form of discrete particles in the flooring material, up to a temperature of at least about 200°C. According to the invention, the organic filler preferably is a polymer material selected from one or more of: starch, cellulose and polyethylene, the polyethylene having a melt index below 0.1 g/10 min (190°C/21.6 kg) and a phase stability to at least about 200°C. When used as fillers, starch and cellulose are advantageous in that they both have fairly high contents of hydroxyl groups, which are cross-linked with the silane groups of the crosslinkable ethylene polymer component. This provides yet another possibility of adjusting the properties of the material. As an example of a preferred polyethylene filler, mention may be made of the polymer marketed under the tradename of Lupolen UHM 201 by BASF and having a density of 0.93 g/cm³ and a melt flow below 0.1 g/10 min (190°C/21.6 kg). This polyethylene filler also contributes to giving the flooring material a harder surface.

Apart from the components mentioned above, the flooring material according to the invention contains certain additives, as appears from the foregoing and will be described in more detail below.

In order to obtain the aimed-at flame resistance, the material contains 0.2-7 parts by weight of a flame retardant, preferably 0.6-4 parts by weight. Even though

conventional flame retardants are not excluded from the flooring material according to the invention, it is especially preferred that the flame retardant is a silicone replacing conventional antimony- or halogen-containing flame retardants. The effect of the silicone is enhanced by combining it with an organic metal salt, more specifically an organic salt of a metal from the group IIA of the Periodic table. Preferably, the organic metal salt is magnesium stearate. The above flame retardant contents include both the silicone and the organic metal salt. Normally, the silicone is present in an amount of 0.1-5 parts by weight, preferably 0.5-3 parts by weight, while the organic metal salt is present in an amount of 0.1-2 parts by weight, preferably 0.1-1 part by weight. In addition to imparting the aimed-at flame-retardant properties to the material, the flame retardant has a lubricating ability, which facilitates the processing of the material and further enhances its impact resistance. As an instance of a preferred flame retardant, mention may be made of the product available under the tradename of SFR 100 Silicone Fluid from General Electric. Further details of this flame retardant are found in US Patent 4,387,176.

Moreover, the flooring material according to the invention contains 0.1-2 parts by weight of an antistatic agent, preferably 0.1-1 part by weight. This is an additive required in order to avoid static charging of the flooring material and to improve the dirt-repellent properties of the finished material. The antistatic agent employed in the flooring material according to the invention can be selected from known antistatic agents, but preferably consists of glycerol stearate, for instance in the form of the product available from Hoechst under the tradename of Hostastat FE-2.

Finally, the flooring material contains a stabiliser, which has a stabilising effect as regards oxidation and decomposition (yellowing), which otherwise may

occur, for instance in the presence of the antistatic agent mentioned above. As an example of a suitable stabiliser, mention may be made of sterically hindered phenols, for instance those available from Ciba under the tradename of Irganox 1010.

Apart from the components indicated above, the flooring material according to the invention may contain optional conventional additives and pigments.

With the composition described above, in particular the lack of inorganic fillers, the flooring material according to the invention have only marginal contents of metals that are questionable or objectionable from the point of view of the environment and are released by leaching, biological-chemical decomposition or combustion, i.e. the content of such metals as aluminium, lead, cadmium, copper, chromium and zinc is basically zero.

The inventive flooring material of the above composition can be produced by using conventional techniques and conventional equipment. There should thus be no need of any detailed description of the production of the flooring material according to the invention. As an example of such production, it may, however, be mentioned that the components and the additives may first be weighed and mixed in cold state, whereupon the resulting mixture is melted and extruded in the form of bands, which are fed to a rolling mill and there are processed to webs. The resulting webs are cut to pieces or crushed and may then immediately be rolled or pressed to form the finished flooring material. Alternatively, the cut or crushed webs may first be stored and then at a suitable moment be heated and rolled or pressed to form the finished flooring material.

The invention will now be further elucidated with the aid of a few non-restricting Examples. The following comparison is based on two apparently equivalent, 2-mm-thick homogeneous flooring materials intended for public use. The one flooring material is produced in accordance

with the invention, while the other flooring material is a PVC-based flooring material of known composition.

The upper side and the lower side of the flooring material according to the invention and the upper side
5 of the PVC-based flooring material were subjected to a corona treatment in order to increase the adhesion. Then, the upper side and the lower side of the flooring material according to the invention were coated with 5 g (based on dry solids) of a primer (based on RIC from PPG
10 Industries) per m². Finally, the one surface (the upper side) of the two flooring materials was coated with 10 g (based on dry solids) of polyurethane (based on NeoRez R-986 from Zeneca Resins) per m². The purpose of this polyurethane layer is to make the flooring materials easier
15 to clean and enhance their dirt-repellent capacity. Since the polyurethane layer affects the wear resistance, the wear-resistance test in Example 1 was also performed on flooring materials having no such surface layer of polyurethane. The other properties of the flooring material
20 are only marginally affected by the polyurethane layer.

The two flooring materials have the following composition.

Flooring Material According to the Invention

<u>Parts by weight</u>	<u>Tradename</u>	<u>Designation</u>	<u>Supplier</u>
47.7	DSH 8501.00	Ethylene- α -olefin copolymerisate	DOW Chemicals
26	Embryon [®] HG770J	Polypropylene	Borealis
8.7	LE 4421	Crosslinkable ethylene polymer	Borealis
0.4	LE 4438	Catalyst	Borealis
13	Lupolen UHM201	UHMW - PE	BASF
1	SFR100	Flame retardant	General Electric
0.7	Parma	Magnesium stearate	Bärlocher
0.5	Hostastat FE-2	Antistatic agent	Hoechst
0.1	Irganox 1010	Stabiliser	Ciba
1.9		Pigment	

PVC-based Flooring Material (Tarkett Eminent from
Tarkett AB

<u>Parts by weight</u>	<u>Tradename</u>	<u>Designation</u>	<u>Supplier</u>
47.1	Norvinyl S6260	PVC	Norsk Hydro Plast AB
17.2	DEHP	Diethylhexyl phthalate	Neste Chemicals
0.7	Lankromark LZ 1694	BaZn Stabiliser	Akcros Chemicals
0.9	Lankroflex EWS	Epoxidised soy- bean oil	Akcros Chemicals
0.3	Tefacid 1 VT65	Stearic acid	Tefac AB
12.6	Strådolomit A30	Dolomite	Stråbruken AB
10.8	Sjöhästen FF	Calcium carbonate	Malmökrita AB
8.4	Kaolin FA	Kaolin	Zavod
2		Pigment	

Example 1

In this Example, the wear resistance of the flooring material according to the invention was compared with that of the prior-art, PVC-based flooring material. The wear resistance was determined according to the standard EN 660.

In the test, the wear resistance of the flooring material according to the invention was found to be 1.4 mm³/100 turns for material having a surface layer of polyurethane and 0.65 mm³/100 turns for material having no such surface layer, whereas the PVC-based flooring material had a wear resistance of 3.38 mm³/100 turns when provided with a surface layer of polyurethane and a wear resistance of 3.06 mm³/100 turns when not provided with such a surface layer. Thus, the flooring material according to the invention had a much better wear resistance than the known PVC-based flooring material.

Example 2

In this Example, the fire propagation and the smoke emission of the flooring material according to the invention and of the prior-art PVC-based flooring material were tested. The test was carried out in accordance with the standard SIS 024825. According to this standard, the fire propagation should be below 55 cm, and the fire emission should be below 30%.

In the test, the flooring material according to the invention was found to have a fire propagation of 40 cm and a smoke emission of 3%, whereas the PVC-based flooring material was found to have a fire propagation of 22 cm and a smoke emission of 16%. Both materials thus had a fire propagation well below the standard limit. However, the flooring material according to the invention gave off very little smoke and much less than the PVC-based flooring material.

In addition to this test, the fire propagation and the smoke emission were tested according to the so-called Radiation Panel Test. According to this test, an accept-

ed material should require a power exceeding 0.45 W/cm^2 for fire propagation, and the material should exhibit a smoke emission below $750\% \cdot \text{min}$.

In this test, the flooring material according to the invention required 0.50 W/cm^2 in order to catch fire and had a smoke emission of $55\% \cdot \text{min}$, whereas the PVC-based flooring material required 0.99 W/cm^2 in order to catch fire and had a smoke emission of $300\% \cdot \text{min}$. Also in this case, both materials had fire-propagation values and smoke-emission values below the standard limit. However, the flooring material according to the invention gave off much less smoke than the PVC-based flooring material.

Example 3

In this Example, the indentation-recovery of the flooring material according to the invention and the PVC-based flooring material were determined in accordance with the standard SIS 923505.

In this test, the flooring material according to the invention had an indentation of 0.88 mm after 5 min and a recovery of 89.8% after 24 h . The corresponding values of the PVC-based flooring material were, respectively, 0.74 mm and 87.8% . Thus, the flooring material according to the invention had a slightly higher indentation value than did the PVC-based flooring material, but this was compensated for by a higher degree of recovery.

Example 4

In this Example, one determined the residues left after combustion of the flooring material according to the invention and the PVC-based flooring material, as well as the deposition requirement created by these combustion residues. The flooring materials were burnt to ashes at 550°C .

The results of the test are indicated in the Table below.

<u>Ashes after combustion</u>			<u>Deposition requirement for ashes and bound chlorine</u>	
Flooring material	kg/m ²	% by weight of starting material	kg/m ²	% by weight of starting material
Invention	0.12	5.9	0.12	5.9
PVC	0.84	27.6	2.4	70

It is evident from this Table that the flooring material according to the invention yields less ash and thus involves much smaller deposition requirements than does the PVC-based flooring material. The much greater deposition requirement of the PVC-based flooring material is, inter alia, due to the addition of lime/dolomite to bind released chlorine.

10 Example 5

This Example aims at demonstrating the content of metals, which are environmentally objectionable and originate from fillers and other additives, found in the flooring material according to the invention and the PVC-based flooring material. Thus, the contents of these metals were determined in ashes from the combustion of the flooring materials by dissolving the ashes in concentrated nitric acid. The dissolution was performed by mixing the ashes and the nitric acid in a container of Teflon[®], whereupon the container was sealed and heated in a microwave oven. Samples that had not been burnt to ashes were used for determining the contents of cadmium and lead. The final determination of the metal contents was performed with the aid of Plasma emission spectrometry (ICP-AES) or Plasma mass spectrometry (ICP-MS). The metal contents determined appear from the Table below.

	Invention g/m ²	PVC g/m ²	Test method
Aluminium	0.002	12	ICP-AES
Lead	0.000	0.015	ICP-MS
Cadmium	0.0000	0.0001	ICP-MS
Copper	0.000	0.003	ICP-AES
Chromium	0.000	0.008	ICP-AES
Zinc	0.00	0.15	ICP-AES

It is evident from the Table that the flooring material according to the invention causes no, or but insignificant, environmental pollution owing to its metal content. It should be pointed out that the PVC-based flooring material has an adverse effect on the environment not only as a result of its metal content but also as a result of the addition of lime/dolomite to bind released chlorine.

CLAIMS

1. A flooring material, characterised in
5 that it comprises
30-70 parts by weight of a copolymer of ethylene and an
 α -olefin having 4-10 carbon atoms,
20-40 parts by weight of polypropylene,
 5-20 parts by weight of a crosslinked ethylene polymer,
10 10-25 parts by weight of an organic filler,
 0.2-7 parts by weight of a flame retardant,
 0.1-2 parts by weight of an antistatic agent, and
 0.1-1 part by weight of a stabiliser,
and that the material is free from inorganic fillers.
- 15 2. A flooring material as set forth in claim 1,
characterised in that it comprises
40-60 parts by weight of a copolymer of ethylene and an
 α -olefin having 4-10 carbon atoms,
25-30 parts by weight of polypropylene,
20 5-15 parts by weight of a crosslinked ethylene polymer,
10-20 parts by weight of an organic filler,
 0.6-4 parts by weight of a flame retardant,
 0.1-1 part by weight of an antistatic agent, and
 0.1-1 part by weight of a stabiliser.
- 25 3. A flooring material as set forth in claim 1 or 2,
characterised in that the α -olefin employed is
octene.
4. A flooring material as set forth in any one of
claims 1-3, characterised in that the cross-
30 linked ethylene polymer is a copolymer of ethylene and an
ethylenically unsaturated silane compound.
5. A flooring material as set forth in claim 4,
characterised in that the copolymer contains
1-30% by weight of the silane compound.
- 35 6. A flooring material as set forth in any one of
claims 1-5, characterised in that the organic
filler is selected from one or more of: starch, cellulose

16

and polyethylene having a melt index below 0.1 g/10 min (190°C/21.6 kg) and a phase stability in the flooring material of at least about 200°C.

7. A flooring material as set forth in any one of
5 claims 1-6, characterised in that the flame retardant comprises a silicone and a an organic metal salt.

8. A flooring material as set forth in claim 7,
characterised in that the organic metal salt
10 is magnesium stearate.

9. A flooring material as set forth in any one of claims 1-8, characterised in that the anti-static agent comprises glycerol stearate.

10. A flooring material as set forth in any one of
15 claims 1-9, characterised in that the stabiliser is a sterically hindered phenol.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 96/01094

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C08L 23/08, C08L 23/12, C08L 51/06, E04F 15/10
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C08L, E04F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, CAPLUS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5276082 A (JOHN S. FORRY ET AL), 4 January 1994 (04.01.94), abstract, column 1, lines 8-12, column 2, lines 27-33 --	1-10
A	EP 0321760 A1 (HÜLS TROISDORF AKTIENGESELLSCHAFT), 28 June 1989 (28.06.89), abstract, page 2, lines 7-11 --	1-10
P,A	EP 0683205 A1 (ELF ATOCHEM S.A.), 22 November 1995 (22.11.95), abstract -- -----	1-10

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

• Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

& document member of the same patent family

Date of the actual completion of the international search

17 December 1996

Date of mailing of the international search report

09 -01- 1997.

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Agneta Österman Wallin

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

28/10/96

International application No.

PCT/SE 96/01094

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
US-A-	5276082	04/01/94	CA-A-	2112529	30/06/95
			DE-A-	4400035	06/07/95
			GB-A-	2285258	05/07/95
			GB-D-	9326571	00/00/00
EP-A1-	0321760	28/06/89	SE-T3-	0321760	
			DE-A-	3743296	29/06/89
			JP-T-	3502705	20/06/91
			US-A-	5244942	14/09/93
			WO-A-	8905835	29/06/89
			DE-A-	3743297	29/06/89
EP-A1-	0683205	22/11/95	CA-A-	2149831	21/11/95
			CN-A-	1113248	13/12/95
			FI-A-	952456	21/11/95
			FR-A,B-	2720072	24/11/95
			JP-A-	7316353	05/12/95